

HyPrint MVI 750

Naphthenic Ink Oil Marketing Specification

This severely hydrotreated naphthenic printing ink oil has a low odor level, and good solvency and volatility.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, SUS at 100°F (37.8°C)	ASTM D2161	730	800	770
Viscosity, SUS at 210°F (98.9°C)	ASTM D2161			65.0
Viscosity, cSt at 40°C (104°F)	ASTM D445	136.6	149.4	144
Viscosity, cSt at 100°C (212°F)	ASTM D445			11.2
API Gravity, 60°F (15.6°C)	ASTM D1250			23.0
Specific Gravity, 60°F (15.6°C)	ASTM D4052			0.9159
Viscosity-Gravity Constant	ASTM D2501			0.852
Density, lbs/gal at 60°F	ASTM D1250			7.627
Density at 15.6°C, g/cm ³	ASTM D1250			0.9152
Molecular Weight	ASTM D2502			445
Flash Point, COC, °F (°C)	ASTM D92	385 (196)		442 (228)
Flash Point, PMCC, °F (°C)	ASTM D93			420 (216)
Color, ASTM	ASTM D6045		2.5	L1.5
Pour Point, °F (°C)	ASTM D5949		12 (-11)	-15 (-26)
Water Content	ASTM D7546M	PASS		PASS
Appearance	ASTM D4176M	PASS		PASS
Chemical Properties				
Aniline Point, °F (°C)	ASTM D611	193 (89)	209 (98)	202 (94)
Health and Safety Properties				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1

HyPrint MVI 750 is a product of Ergon Refining, Inc.
February 21, 2017